

TECHNICAL DATA

ISOPRIME 21

Chemical Composition	: Moisture-curing isocyanate prepolymer
Physical Appearance	: Clear, light-amber liquid
Solid Content	: 30% by mass
Solvent Blend	: Aliphatic & Aromatic mixture
Specific Gravity	: 0.92 – 0.94 @ 25 Celsius
Viscosity (Brookfield)	: 3 Centipoises at 25 Celsius
Flash Point (COC)	: 24 – 28 Celsius
Application	: Solvented polyurethane primer for concrete & steel
Theoretical Coverage	: 5 – 6 square meters per kilogram (concrete) 6 – 7 square meters per kilogram (steel)

Revised: 15.01.2023

Technical information, data are to be considered as typical values and not sales specification. Actual measured values may vary due to factors beyond our control. Indications concerning function and application of the products are empirical. Although the information is believed to be accurate, there is no warranty by ISOLA. None of the recommendations becomes part of the warranted quality of the products. Due to the fact that the conditions of individual use are beyond ISOLA's direct and continuous control, ISOLA disclaims all responsibility in connection with the use of its products and does not warrant against any loss direct or consequential

ISOLA SOLUTIONS W.L.L

P.O. Box 530, Manama, Kingdom of Bahrain, Tel: 17784777, Fax:17911422, Email: isola@hajihassan.com, web: www.isolasolutions.com